



Crown Tropical Latex

Basic Uses: interior/ exterior surfaces

LATEX PAINT



TECHNICAL DATA

VISCOSITY: 108-113 KU's (KREBS UNITS)
WEIGHT/GALLON: 10.37 + .10 lbs.
SOLIDS (WEIGHT): 50%
GRIND: 6 minimum
DRY FILM THICKNESS: At a rate of 125
ft²/gal: 4 mil dry, 1.7 mils wet

SIZES

1 gallon
5 gallons

FINISH

Flat (0-5%) @
Geometry 60°

COLOR

White
Bone white

DESCRIPTION

A latex paint for interior or exterior concrete, wood or masonry surfaces, such as basements and other floors, patios, porches, steps, breezeways, playrooms, etc. Crown meets TT-P-29K

DRYING TIME

hard in six (6) hours. Allow at least twelve (12) hours and preferable overnight for recoating. Set-To-Touch between 20-30 minutes @ 77°F and 50% R.H.

APPLICATION

SURFACE PREPARATION:

All surfaces should be sound, clean and free of oil, grease, loose or peeling paint, and other foreign substances.

PREVIOUSLY PAINTED SURFACES:

Can be used over either oil or latex painted surfaces. Either surface must be clean to obtain proper adhesion.

METHOD OF APPLICATION:

Brush, 3/8" (9.52 mm) nap of roller or spray. On sound, repainted surfaces, one coat is usually sufficient. Certain shades or oranges, yellows and pinks may require a second coat for uniform color.

THINNING:

Not recommended. Do not mix with solvent or solvent thinned paints.

COVERAGE:

250-400 sq. ft. per gallon, depending on surface texture and porosity.

CLEAN UP:

Wipe off drips and spatters using a wet cloth with soap and water. Clean equipment with soapy water.

PRECAUTIONS

Do not apply if temperature of air or surface is below 50 °F (10°C). Stop painting at least two (2) hours before you expected dew to form, rain or the temperature to drop. KEEP FROM FREEZING! CAUTION: Do not take internally. Close container after each use.

KEEP OUT OF THE REACH OF CHILDREN!