

# HARRIS®

## Tung • O • Var Marine Clear Spar Varnish

Basic Uses: interior/exterior wood surfaces

VARNISH



### TECHNICAL DATA

VISCOSITY: 60-65 KU's  
WEIGHT/GALLON: 7.75 lbs/gal  
FLASH POINT: Above 100°F  
SOLIDS (WEIGHT): 58%  
SOLIDS (VOLUME): 50%  
DRY FILM THICKNESS:  
1.0 mils per coat (calculated)

### SIZES

1 gallon (3.785 Liters)  
1 quart (.95 Liters)  
½ pint (236 ML)

### FINISH

Gloss (90% @ 60°)

### COLOR

Clear

### DESCRIPTION

Tung-O-Var Marine Spar Varnish is a phenolic modified clear gloss all-purpose varnish that is suitable for use on all exterior/interior wood surfaces such as siding, doors, trim, floors, paneling, furniture, cabinets, counter tops, etc. This is Harris Paints performance alternate to Federal Specification MIL-V-1174b.

### COMPOSITION AND PROPERTIES

Tung-O-Var Marine Spar Varnish is based on a Phenolic modified synthetic resin. It dries to a very hard and tough film with excellent resistance to abrasion, marring, chipping, detergents, washing, foodstuffs, grease, oil and water.

### APPLICATION

#### SURFACE PREPARATION:

Surface preparation requirements must be followed closely. Apply one (1) coat of HARRIS® Sanding Sealer.

#### NEW SURFACES:

Sand well, dust clean and finish with 2 coats of HARRIS® Marine Spar Varnish Clear.

#### PREVIOUSLY FINISHED SURFACES:

For best results, remove all finishes back to bare wood and refinish as for new work. For recoating over sound, aged finishes, first remove all wax, grease, oil or other foreign matter by washing with paint thinner and then with water and detergent. When surface is clean apply two (2) coats of this product, sanding lightly between coats.

#### METHOD OF APPLICATION:

Brush, spray or roller. (Apply in thin, uniform coats).

#### THINNING:

Normally no thinning is required. If required, use up to 1/2 pint of mineral spirits per gallon.

#### COVERAGE:

Approximately 650 sq. ft. per gallon on smooth sealed surfaces.

#### DRY TIME:

At 60°-80°F and 50% R.H. it dries to touch in three (3) hours and hard in six (6) hours. Allow at least twelve (12) hours and preferable overnight for recoating.

#### CLEANUP:

Clean up drips, spatters and equipment with HARRIS® Paints Puritine Mineral Spirits.

### PRECAUTIONS

**CAUTION!** Combustible. HARMFUL IF INHALED

Keep away from heat and open flame. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation.

Do not take internally.

**KEEP OUT OF THE REACH OF CHILDREN.**