

## TECHNICAL DATA DIGEST

### HARRIS GALVANIZED METAL PRIMER WHITE

BASIC USES:	It is a medium oil, alkyd-based primer specifically formulated for good adhesion to galvanized steel and aluminum for interior or exterior. Also for interior, steel non-corrosive areas, such as warehouses, etc. Topcoats may be oil, alkyd, epoxy ester or latex based.
COMPOSITION AND PROPERTIES:	This white alkyd base primer contains no lead pigments or lead dryers.
LIMITATIONS:	Not recommended on exterior un-galvanized steel.
SIZES:	1-gallon containers
FINISH:	Flat
COLOR:	White, (slightly gray)
<u>TECHNICAL DATA</u>	
VISCOSITY:	70-80 Ku's (KREBS-STORMER)
WEIGHT/GALLON:	10.70 ± 5 lbs/gal
FLASH POINT:	Above 80 <sup>0</sup> F
SOLIDS (WEIGHT):	Approximately 70.5%
SOLIDS (VOLUME):	Approximately 49.9%
DRY FILM THICKNESS:	3 mils wet; 1.5 mils dry

## APPLICATION

### SURFACE

#### PREPARATION:

All surfaces must be clean, dry and free of oil, grease, dirt, chemicals, rust and other foreign materials.

#### NEW METAL:

Prime with this product.

### PREVIOUSLY

#### PAINTED METAL:

Rusted or abraded areas should be thoroughly wire-brushed or power-cleaned, then spot-primed with this product. A full coat of primer may then be applied, if desired, depending on the color of the finish coat.

#### TINTING:

Up to 2 fl. oz. Harris Tint Colorants per gallon.

#### THINNING:

No thinning required for brushing. For conventional spray, thin with up to 10% per gallon of V. M. & P Naphtha or Mineral Spirits.

### METHOD OF

#### APPLICATION:

Brush, roll or spray.

#### COVERAGE:

400-529 sq. ft. per gallon, depending on method of application.

#### DRY:

To touch in one (1) hour at 60<sup>0</sup>- 80<sup>0</sup>°F; to recoat overnight.

#### CLEANUP:

Use mineral spirits.

#### PRECAUTIONS:

**CAUTION!** Combustible. Keep away from heat and open flame. Do not smoke. Avoid prolonged contact with skin and breathing of vapor or spray mist. Close container after each use. Use with adequate ventilation. **KEEP OUT OF THE REACH OF CHILDREN.**