



HEAT RESISTANT ENGINE ENAMEL



SPRAY PAINT

Basic Uses: interior/exterior for metal use (resists up to 500°F)

TECHNICAL DATA	SIZES	FINISH	COLOR
<p>VISCOSITY: 15-20 KU's FLASH POINT: Less than 156° F SOLIDS (WEIGHT): 45.73% (varies with colors) SOLIDS (VOLUME): 30.78% (varies with colors) DRY FILM THICKNESS: 1.05 mils dry recommended DRYING TIME: Set to touch in 20 minutes</p>	<p>11 ounce can</p>	<p>GLOSS FLAT PRIMER</p>	<p>Caterpillar Yellow, Cast Iron Gray, Rebuilder Gray, Universal Gray, High Temp. Aluminum, Gold, Chevrolet Orange & Blue, Ford Red & Blue, Universal Black, Cummings Beige, Clear</p>

DESCRIPTION

Quick drying enamel that gives surfaces protection and industry.

APPLICATION

SURFACE PREPARATION: Thoroughly clean all grease, oil, dirt, wax and rust scale from surface before painting.

NEW METAL SURFACE:

New or rusted areas should be primed with Aerosol Primer before painting.

PREVIOUSLY PAINTED SURFACES:

Make sure surface is free of dirt, grease, wax and rust scale from surface before painting. Use drop cloth or newspapers to protect surrounding areas from spray mist. Surface temperature must be above 65° F from painting. Do not paint in high winds or excessively high humidity.

SURFACES IN GOOD CONDITIONS:

Spray directly on bare areas. Primers are not necessary.

SURFACES IN POOR CONDITIONS:

Remove all rust and peeled or blistered paint to restore back to sound surface. Then, applied in all surfaces the Gray Primer allow 30 min. to dry.

METHOD OF APPLICATION:

Shake can until agitator ball begins to rattle and continue to shake for one min. after. Occasionally shake during use. Hold can 12 to 16 inches from surface to be sprayed and apply several thin coats rather than one heavy coat. Recoat after one hour.

PRECAUTION

CAUTION! EXTREMELY FLAMMABLE. KEEP OUT OF REACH OF CHILDREN. Vapors may ignite explosively. Prevents buildup vapor. Keep from heat, sparks, flames or other heat sources. Do not smoke. To avoid breathing vapors or spray mist, open windows and doors or use other means to ensure fresh air entry during application and drying. If you experience eye watering, headaches or dizziness, increase fresh air or wear respiratory protection or leave the area.

(Continued)

Tung • O • Var Marine Clear Spar Varnish

